


CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" saxony Tufté 1/10" saxony Getuftet 1/10" saxony Getuft 1/10" saxony
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PA 6 IMPREL®
PRIMARY BACKING SUPPORT TRÄGERMATERIAL TUFTDOEK	Non woven PES Non tissé Vlies Felt
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Action Back
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	Ca. 1.150 gr/m ²
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	Ca. 2.095 gr/m ²
PILE HEIGHT EPAISSEUR DU VELOURS POLHÖHE POOLHOOGTE	Ca. 5 mm
TOTAL HEIGHT EPAISSEUR TOTAL GESAMTHÖHE TOTALE DIKTE	Ca. 7 mm
TUFT DENSITY NOMBRES DE POINTS NOPPENZAHL AANTAL PUNTEN	Ca. 209 000/m ²
PILE DENSITY DENSITÉ DU VELOURS POLROHDICHTHE POOLDICHTHEID	Ca. 0.157 g/cm ³
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 33 - LC4
UPEC	U3s P3 E1 C0 Certification CSTB: 10/273
CASTOR CHAIR SUITABILITY CHAISE À ROULETTES STUHLROLLENEIGNUNG ROLSTOELGESCHIKTHEID	EN 985 A: intensive use
STAIR SUITABILITY ESCALIERS TREPPENEIGNUNG TRAPPENGESCHIKTHEID	EN 1963 A: intensive use


PERMANENTLY ANTISTATIC ANTISTATIC PERMANENT PERMANENT ANTISTATISCH PERMANENT ANTISTATISCH	ISO 6356 ≤ 2 kV
IMPACT NOISE RATING ISOLATION PHONIQUE TRITTSCHALLVERBESSERUNG GELUIDSISOLATIE	ISO 140-8 26 dB ΔLw
SOUND ABSORPTION ABSORPTION PHONIQUE SCHALLABSORPTIONSGRAD GELUIDSABSORPTIE	ISO 354 0.20 αw
THERMAL RESISTANCE RÉSISTANCE THERMIQUE WÄRMEDURCHLASSWIDERSTAND WARMTEDOORLAATWEERSTAND	ISO 8302 0.09 m ² K/W
FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	ISO 105-B02 ≥ 5-6
COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 Bfl-s1 (if glued)
RUBBING FASTNESS SOLIDITÉ AU FROTTEMENT REIBECHTHEIT WRIJFECHTHEID	EN ISO 105-X12 ≥ 4
WIDTH LARGEUR BREITE BREDTE	EN ISO 3018 ca. 400 cm





TUV NORD
Systems
Voc NOISE System
Green & Co. 10
Voc NOISE System
Green & Co. 10


GUT TESTED
ENVIRONMENT CARPETS TESTED FOR A BETTER LIVING ENVIRONMENT


UPEC
moquettes touffetées et tissées en lés
<http://evaluation.cstb.fr>
































EN14041







CE

16

Balta Industries - Kanegem-
straat 15 - BE 8700 Tielt

DOP: 1011#1E0ABV

Textile Floor Covering EN1307
Notified body 2401

www.baltamediabank.com


REG. NR
F8CC85E8

EAC

www.pro-dis.info



▲ 16



▲ 79

▲ 72

▲ 43

▲ 94

↔ **ca.80 X** ↓ **ca.80 CM**

 **arc edition**
performance flooring