


RADICI PIETRO INDUSTRIES & BRANDS S.p.A.



CITY



Specification in according EN 1307

Costruzione	Technique de fabrication	Construction	Herstellungsverfahren
Moquette Wilton superficie velluto-riccio	Moquette Wilton à velours coupé/bouclé	Wilton carpet cut/loop pile	Wilton teppich schnittschlingenpol
Composizione	Composition du velours	Pile composition	Polnutschicht
100% Lana	100% Laine	100% Wool	100% Wolle
Sottofondo	Dossier	Secondary backing	Rückenausrüstung
Juta naturale/sintetico	Jute naturel/synthétique	Natural jute/synthetic	Naturjute/synthetik
Punti al m²	Touffes au m²	Stitches per m²	Knoten m²
± 93000	± 93000	± 93000	± 93000
Altezza pelo	Hauteur du velours	Pile height	Polhöhe
± 7 mm	± 7 mm	± 7 mm	± 7 mm
Altezza totale	Hauteur totale	Total height	Gesamtdicke
± 9 mm	± 9 mm	± 9 mm	± 9 mm
Peso della fibra	Poids du velours	Yarn weight	Polgewicht
± 1248 g/m ²	± 1248 g/m ²	± 1248 g/m ²	± 1248 g/m ²
Peso totale	Poids total	Total weight	Gesamtgewicht
± 2234 g/m ²	± 2234 g/m ²	± 2234 g/m ²	± 2234 g/m ²
Larghezza rotolo	Largeur du rouleau	Roll width	Breite
400 cm	400 cm	400 cm	400 cm
Famiglia Wilton 100% lana	Famiglia Wilton 100% lana	Famiglia Wilton 100% lana	Famiglia Wilton 100% lana



Colour fastness to light	≥ 5 (4 pastel shade)	Thermal resistance m ² K/W	≤ 0,17
Insulation impact noise ΔLw	32 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,23		

RESISTENZA – WEARABILITY RESISTANCE - STRAPAZIERWERT				COMFORT – COMFORT CONFORT - KOMFORTWERT			
estrema extreme extrême extrem	elevata high élevée stark	normale good normale normal	sufficiente normal suffisante gering	medio medium moyen einfach	buono good bon gut	alto very good élevé hoch	ottimo excellent excellent luxuriös

Approved by Technique Management: M. Medica

Emission date: 14/11/2012