

FACTS

Thickness

EAN Code

Installation method



OAK JOHAN

The natural oil stain on this single-strip oak floor from the Founders Collection enriches its golden-brown finish, and accentuates the knots and cracks of the timber for a truly rustic expression. Each board is carefully brushed to bring out the character of the grain and highlight the texture of the wood. Four-sided bevelling at the edges ensures a classic full plank look and feel. Hand-scraping enhances the worn appearance of the floor.

| PRODUCT DESCRIPTION | | |
|-----------------------|---|--|
| Article Number | 151N7BEKF0KW240 | |
| Surface treatment | Oil | |
| Design features | Bevelled 4-sided, handscraped, brushed | |
| Dimensions | 2420 x 187 x 15 mm | |
| Weight per Package | 22 kg | |
| Area per Package | 2.72 m² | |
| Area Per Board | 0.453 m² | |

DETAIL DESCRIPTION

All naturally occuring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

COLOUR CHANGE

Some muting of colour variation to medium, straw brown.

| Wood Species | Oak | |
|----------------------|---------------------|--|
| Board | 1-strip | |
| Grading | Dynamic | |
| Range | Kährs Original | |
| Collection | Founders Collection | |
| Resandable | 2-3 times | |
| Natural/Stained | Natural | |
| Brinell Value | 3,7 | |
| Joint | Woodloc® 5S | |
| Roor heating | Yes | |
| Warranty | 30 years | |
| Wear-layer material | Hardwood | |
| Wear-layer thickness | 3, 5 mm | |
| Core material | Pine/Spruce lamella | |

15 mm

Floating, glue-down

7393969036023

TECHNICAL PROPERTIES

| Moisture content | EN13183 | 7%±2% |
|----------------------------|-------------|-------------|
| Minimun Mean Density kg/m³ | | >500 kg/m³ |
| Reaction To Fire | EN13501-1 | Dfl-s1 |
| Formaldehyde Emission | EN717-1 | E1 |
| Content PCP | CEN/TR14823 | ≤ 5 x 10-6n |
| Breaking Strength N/mm² | EN1533 | NPD |
| Thermal Conductivity | EN12664 | 0,14 W/mK |
| Thermal Resistance R-Value | | .11 (m2K/W) |
| Biological Durability | EN350-2 | Class 1 |
| CARB2 | | Compliant |
| | | |

CERTIFICATES

