

OAK MÖRE

The even grey stain on this single-strip oak floor from the Småland Collection allows the warmer nuances in the wood to seep through, resulting in a calm and balanced expression. Each board is carefully brushed to bring out the character of the grain and highlight the natural texture of the wood. Four-sided bevelling at the edges ensures a classic, full plank look and feel. Every board is meticulously hand-scraped, which enhances the rustic appearance of the floor.

PRODUCT DESCRIPTION		
Article Number	151NCSEK03KW240	
Surface treatment	Oil .	
Design features	Bevelled 4-sided, brushed, handscraped	
Dimensions	2420 x 187 x 15 mm	
Weight per Package	22 kg	
Area per Package	2.72 m²	
Area Per Board	0.453 m²	

DETAIL DESCRIPTION

All naturally occuring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

COLOUR CHANGE

Stained product - noticable color change over time.

FACTS	
Wood Species	Oak
Board	1-strip
Grading	Dynamic
Range	Kährs Supreme
Collection	Småland Collection
Resandable	2-4 times
Natural/Stained	Stained
Brinell Value	3,7
Joint	Woodloc® 5S
Roor heating	Yes
Hoor heating Warranty	Yes 30 years
Warranty	30 years
Warranty Wear-layer material	30 years Hardwood
Warranty Wear-layer material Wear-layer thickness	30 years Hardwood 3, 5 mm
Warranty Wear-layer material Wear-layer thickness Core material	30 years Hardwood 3, 5 mm Pine/Spruce lamella
Warranty Wear-layer material Wear-layer thickness Core material Backside material	30 years Hardwood 3, 5 mm Pine/Spruce lamella Veneer
Warranty Wear-layer material Wear-layer thickness Core material Backside material Thickness	30 years Hardwood 3, 5 mm Pine/Spruce lamella Veneer 15 mm

TECHNICAL PROPERTIES

Moisture content	EN13183	7%±2%
Minimun Mean Density kg/m³		>500 kg/m ³
Reaction To Fire	EN13501-1	Dfl-s1
Formaldehyde Emission	EN717-1	E1
Content PCP	CEN/TR14823	≤ 5 x 10-6n
Breaking Strength N/mm²	EN1533	NPD
Thermal Conductivity	EN12664	0,14 W/mK
Thermal Resistance R-Value		.11 (m2K/W)
Biological Durability	EN350-2	Class 1
CARB2		Compliant

CERTIFICATES

